

CLAIMS

1. An aluminum flake pigment comprising aluminum flakes as basic particles,
wherein said aluminum flakes have an average particle diameter in the range of 3 to 20
5 μm and an average value of minimum diameters/maximum diameters of at least 0.6.

2. The aluminum flake pigment according to claim 1, wherein the average
aspect ratio of aluminum flakes, included in said aluminum flakes, having diameters of
not more than 10 μm is in the range of 8 to 20.

3. The aluminum flake pigment according to claim 1, wherein said aluminum
flake pigment is a leafing type aluminum flake pigment, and the average value of fatty
acid adsorption amounts on the surfaces of said aluminum flakes is 0.0008 to 0.002
mole/ cm^2 .

4. A method of manufacturing the aluminum flake pigment according to claim
1, comprising a step of flaking aluminum powder in an organic solvent with a grinder
comprising grinding media containing spherical media comprising a material including
steel having diameters in the range of 0.3 mm to 1.5 mm.

5. The method of manufacturing the aluminum flake pigment according to
claim 4, wherein the average particle diameter ($D_{50\text{Al}}$) of said aluminum powder is in
the range of 1.0 to 10.0 μm .

6. A paint containing the aluminum flake pigment according to claim 1 and a
binder.

7. Ink containing the aluminum flake pigment according to claim 1 and a binder.